



TMTD Data Sheet

Item	Powder	Oil powder	Granular
Appearance	White or light gray powder	White or light gray oily powder	White or light gray granular
Initial M.P. (Min) \geq °C	142.0	142.0	142.0
Loss on drying (Max) \leq %	0.30	0.40	0.40
Ash (Max) \leq %	0.30	0.40	0.40
Residue on 150 μ m sieve (Max) \leq %	0.10	0.10	-
Granular diameter mm	-	-	1.0-3.0
Broken strength N	-	-	2-5
Oil content, %	-	1.0-2.0	-

